


# SOLVENT



## SOLVENT

DÖRKEN Solvent sets standards in toning technology for solvent-based varnish systems – and that for various areas of application. The very colourful selection of organic and inorganic pigments offers high coverage and a wide range of colours of maximum brilliance as well as high light stability and weather resistance. With the integration of transparent iron oxides in solvent-based glazes real wood colours can be perfectly reproduced.

## SPECIAL FEATURES

- › compatible with solvent-based thin to thick-layer wood glazes, oils and varnishes
- › selection of very colourful organic and inorganic pigments for real wood colours
- › high coverage even when adding less than 10% of paste to transparent basic materials
- › UV radiation resistant and non-yellowing in long-term tests
- › to be used with Universal and Aqua pastes in one toning system

# SPECIFICATIONS

	Colour	Colour Index	Pigment Content	Ø Density	BFS Data Sheet	Light Stability	Weather Resistance	Resistance to Alkalis	Resistance to Acids
<b>Solvent - inorganic pigments</b>									
<b>311</b>	White	PW 6	74	2.16	1	N/A	N/A	x	x
<b>312</b>	Yellow BiVa G	PY 184	60	2.06	2   1	8	4-5	x	x
<b>354</b>	Yellow Oxide	PY 42	65	1.84	1	8	5	x	x
<b>358</b>	Terracotta	PR 101	37	1.34	1	8	5	x	x
<b>751</b>	Yellow Oxide Transp.	PY 42	45	1.36	1	8	5	x	x
<b>752</b>	Red Oxide Transp.	PR 101	37	1.34	1	8	5	x	x
<b>Solvent - organic pigments</b>									
<b>315</b>	Orange Y	PY 170	36	1.05	2	7-8	4	x	x
<b>317</b>	Red	PR 254	36	1.07	2	8	4	x	x
<b>321</b>	Blue R	PB 15:2	16	1.25	2	8	4-5	x	x
<b>333</b>	Yellow	PY 74	40	1.05	3	6-7	3	x	x
<b>339</b>	Purple	PV 23	13	1.07	3	8	4	x	x
<b>343</b>	Green	PG 7	20	1.13	2	8	4-5	x	x
<b>345</b>	Black	PBk 7	13	1.13	2	8	5	x	x
<b>359</b>	Magenta	PR 122	20	1.00	3	7-8	4-5	x	x

